

## "INTER-TREATMENT" DEGREASING COMPOUND FOR ANY METALS

### **Approvals and conformities**

*EADS / AIRBUS France*

*EUROCOPTER*

*DGA (French Army)*

*BOEING*

*ASN 42203*

*Fiche identification n° 3524 - AIR 0011*

*BAC 5749 (conform)*

**COMORAL DXP is intended for the degreasing by spraying of steel, cast iron, copper, aluminium and alloys, magnesium and titanium.**

- COMORAL DXP is a safe product as it is absolutely free from components likely to present a danger for users. It does not contain nitrite (toxic), nor soda, nor potash (corrosive), nor solvent (flammable).
- This is an economical degreaser, usable at a low temperature (40 to 80° C / 104 to 176° F), at very low concentrations (2 to 5 % on average). It offers a protection for sheltered pieces in storage without requiring a subsequent treatment, nor any rinsing.
- COMORAL DXP is biodegradable, immediately miscible in water and contains surfactants necessary for an optimum degreasing.
- This is a low foaming product whatever the pressure is, with an easy implementation; contact time from 2 to 5 minutes. The salting-out power of the oils makes the maintenance of machines vats and tanks easy ; the bath standing is merely done by a rapid dosage (alkalinity or conductivity).

### ***DIRECTIONS FOR USE***

---

- The required concentration depends on the degree of soiling to be removed. The most satisfactory values in most cases are the following: temperature from 40 to 45° C (104 to 113° F), concentration 3 %, contact time from 4 to 5 minutes.
- As for all degreasing alkaline products, the users likely to come into contact with the product are advised to wear protection (gloves, work aprons, etc...).

### ***TECHNICAL CHARACTERISTICS***

---



Support technique International / International Technical Support  
tel. +33 (0)2 97 43 76 90 fax +33 (0)2 97 54 50 26 E-mail Support@socomore.com  
Pour connaître notre correspondant le plus proche / To find our nearest correspondent  
socomore@socomore.com

**socomore**  
*finishing solutions*

Odour .....	low
Density .....	(at 20°C) 1.14
pH .....	(at 1%) 9.8
Flash point .....	(ISO 2719) none

## ***PRECAUTIONS FOR USE AND STORAGE***

---

A slight deposit may appear in time during storage, which does not damage the quality of the product at all.

Please read the safety data sheet for further information.

**This technical data sheet replaces and cancels the previous one.**

The above details have been compiled to the best of our knowledge, they have, however, an indicative value only, and we therefore make no warranties and assume no liability in connection with any use of this information, particularly if a third party's rights are affected by the use of our products. The above information has been compiled based upon tests carried out by Socomore ; all data is subject to change as Socomore deems appropriate. The data given is not intended to substitute for any testing you must conduct in order to determine the suitability of the product for your particular purposes. Please check your local legislation applicable to the use of this product. Should you need any further information please contact our services.



Support technique International / International Technical Support  
 tel. +33 (0)2 97 43 76 90 fax +33 (0)2 97 54 50 26 E-mail Support@socomore.com  
 Pour connaître notre correspondant le plus proche / To find our nearest correspondent  
 socomore@socomore.com

