

### Approvals and conformities

AMS 2641  
AMS 3046  
ASME  
ASTM-E-1444  
EDF (PMUC : Produits et Matériels Utilisables en Centrale)  
ISO 9934-2  
NFF 00-090  
RCC-M

### MANUFACTURER : BabbCO (Fr)

### DESCRIPTION /APPLICATION(S) :

Fluorescent magnetic detecting medium :

- very fine
- very stable
- spray canned

May be used in any MPI (Magnetic Particle Inspection) technique : current flow, electromagnets, permanent magnets, etc...

### ***DIRECTIONS FOR USE***

It is better to remove any paint residue, oxide, welding powder, which could give false indications.

Part degreasing is suggested.

Shake B 101C can until ball inside is clearly heard.

For 3 to 5 seconds spray B 101C while magnetizing the part.

Let magnetizing on for 2 or 3 seconds after spraying ends so as to "glue" the particles.

Inspect using a UV-A source giving at least 1500  $\mu\text{W}/\text{m}^2$  on the surface under inspection, in a darkened area (visible light level less than 20 lux), after a 2 to 3 minutes adaptation period for the operator's eyes (refer to ISO 3059)

## **TECHNICAL CHARACTERISTICS**

---

- Carrier liquid : aliphatic hydrocarbon
- Propelling agent : CO<sub>2</sub>

Halogenous content ..... < 200ppm  
Sulfur content ..... < 200ppm  
Granulometry ..... 0,5-10 $\mu\text{m}$  / average size 4  $\mu\text{m}$   
Flash point ..... > 60°C

## **PRECAUTIONS FOR USE AND STORAGE**

---

**Transport / Handling** :Refer to Material Safety Data Sheet (MSDS).

**Storage** : Keep away from moisture

Temperature range : -5°C à 50° C (23°F to 122°F).

Keep packaging closed after taking out some of the product

**This technical data sheet replaces and cancels the previous one.**

The above details have been compiled to the best of our knowledge. They have, however, an indicative value only and we therefore make no warranties and assume no liability in connection with any use of this information, particularly if a third party's rights are affected by the use of our products. The above information has been compiled based upon tests carried out by SOCOMORE. All data is subject to change as Socomore deems appropriate. The data given is not intended to substitute for any testing you must conduct in order to determine the suitability of the product for your particular purposes. Please check your local legislation applicable to the use of this product. Should you need any further information please contact us.