

Approvals and conformities

AMS 3044

ASME

ASTM-E-1444

EDF (PMUC : Produits et Matériels Utilisables en Centrale)

ISO 9934-2

MANUFACTURER: Babb Co (F)

DESCRIPTION / APPLICATION(S):

Fluorescent magnetic detecting medium available in spraycan and concentrate to be diluted in water at 5.0 % by volume (1:20).

It is a very fine and stable product containing anticorrosion, wetting and dispersing additives.

Non-flammable propellant

Very low odor

Very low sulfur and halogens contents

Temporary frost resistance, down to -10 °C (concentrate form)

This product can be used with any magnetic field generator (current passing, hand yokes, permanent magnets) and in magnetic bench.

Companion products: Tap water, demineralized water or unconditioned demineralized water (SED grade for Electricity of France)

DIRECTIONS FOR USE

BabbCoSafe 778B can be used from 0 to 50 °C but the best results are achieved between 10 and 35 °C.

Preparation :

We advise to clear the piece from any paint, oxide, soldering flows, etc., likely to give false indications, and to degrease carefully and thoroughly.

- For the concentrate dilution :

Shake thoroughly the product before pour it in a suitable container. Rinse the packaging twice with water and then adjust the final volume according the following data.

Packaging of concentrate : X L

Volume of « ready to use » : 20 * X L

Shake again in order to disperse all the particles. In machine let the pump run for at least 30 minutes before use. The product is then ready for use.

- For the spraycan :

The product is ready to use, shake the can until you can clearly hear the ball tinkling.

Application :

Spray BabbCoSafe 778B during 3 to 5 seconds on the area to be inspected during the magnetization. Continue magnetisation for 2 to 3 seconds after you stop spraying.

Observation :

Inspection is done under UV-A light (minimum irradiance: 1000 W/cm², recommended irradiance: 1500 W/cm²) with low residual visible light (< 20 lux) and after adaptation of the eye for 2 to 3 minutes according EN ISO 3059 standard.

The use of actinic blue (A-Blue®) is possible.

TECHNICAL CHARACTERISTICS

Particle content	1,6 g/L (spraycan and diluted)
Particles dimensions	2 to 10 µm (Average value 3,5 µm)
Powder fluorescent coefficient	4,3 cd/W (under UV-A)
pH	9 (when diluted)
Specific gravity	1,08 (when diluted)

This technical data sheet replaces and cancels the previous one.

The above details have been compiled to the best of our knowledge. They have, however, an indicative value only and we therefore make no warranties and assume no liability in connection with any use of this information, particularly if a third party's rights are affected by the use of our products. The above information has been compiled based upon tests carried out by SOCOMORE. All data is subject to change as Socomore deems appropriate. The data given is not intended to substitute for any testing you must conduct in order to determine the suitability of the product for your particular purposes. Please check your local legislation applicable to the use of this product. Should you need any further information please contact us.