

Approvals and conformities

ASME
RCC-M
ISO 9934-2
ASTM-E-1444
AMS 2641
AMS 3041

MANUFACTURER : BABB CO (Fr)

DESCRIPTION / APPLICATION(S) :

Ready-to-use red medium, primarily designed to be used on worksites under daylight, without a contrasting white background, or under UV-A radiation for more thorough detection. Product is ready to use when shipped.

Companion products : none

DIRECTIONS FOR USE

If need be, grind or smoothen the surface to be inspected.

Shake the canister vigorously before taking out the product.

Spray the product during magnetization, and maintain the magnetization for 2 to 3 seconds after spraying.

Inspect either under white light, actinic blue light or under UV-A lighting under appropriate conditions, regarding standard EN ISO 3059. Discontinuities appear in reddish orange.

TECHNICAL CHARACTERISTICS

Flash point	> 100 °C
Particle content	> 5 g/L
Particles dimensions	0,5 to 25 µm / average 6,5µm
Settlement rate	1.7 to 2.4 mL for 100 mL after 60 minutes.

1 Date : 06-07-2017 Written and checked by : F. Héron

PRECAUTIONS FOR USE AND STORAGE

Transport / Handling: refer to MSDS (material safety data sheet)

Storage : Keep away from light in a reasonably ventilated room.

Limit temperature: 0 to 50°C, if possible keep at a temperature below 25°C.

This technical data sheet replaces and cancels the previous one.

The above details have been compiled to the best of our knowledge. They have, however, an indicative value only and we therefore make no warranties and assume no liability in connection with any use of this information, particularly if a third party's rights are affected by the use of our products. The above information has been compiled based upon tests carried out by SOCOMORE. All data is subject to change as Socomore deems appropriate. The data given is not intended to substitute for any testing you must conduct in order to determine the suitability of the product for your particular purposes. Please check your local legislation applicable to the use of this product. Should you need any further information please contact us.